

NICKWOOD

COLORES | BEIGE | MARRONE



MURO



SRI



INTERIOR



RESIDENCIAL



RECTIFICADO



JUNTA
2mm



24
CARAS

HECHO EN POLONIA

COLLECTION NAME	COLOUR	BODY	SURFACE
NICKWOOD	MARRONE, BEIGE	COLOUR BODY	STRUCTURE

PHYSICAL PROPERTIES		NORM	REQUIREMENTS	MEAN VALUE ACHIEVED	
	WATER ABSORPTION [%]	PN-EN ISO 10545-3	< 0,5	< 0,1	
	MODULUS OF RUPTURE [N/mm ²]	PN-EN ISO 10545-4	≥ 35	≥ 45	
	BREAKING STRENGTH [N]	PN-EN ISO 10545-4	> 700	> 1300	
	FROST RESISTANCE	PN-EN ISO 10545-12	required	resistant	
	ABRASION RESISTANCE	PN-EN ISO 10545-7	required	BEIGE	14/12000
				MARRONE	13/1500
	RESISTANCE TO HOUSEHOLD CHEMICALS	PN-EN ISO 10545-13	min. B	Ammonium chloride solution	A
				Sodium hypochlorite solution	A
	RESISTANCE TO HIGH OR LOW CONCENTRATION OF ACIDS OR ALKALIS	PN-EN ISO 10545-13	declared	Hydrochloric acid solution, 3%	LA
				Citric acid solution 100g/l	LA
				Potassium hydroxide solution, 30g/l	LA
				Hydrochloric acid solution, 18%	HA
				Lactic acid solution, 5%	HA
				Potassium hydroxide solution, 100g/l	HA
	RESISTANCE TO STAINING	PN-EN ISO 10545-14	min. 3	5	
	CRAZING RESISTANCE	PN-EN ISO 10545-11	required	resistant	
DCOF		ANSI A326.3	> 0,42	0,48	
		PN-EN ISO-10545-9	required	resistant	

REFERENCE DOCUMENT: DECLARATION OF PERFORMANCE NO. 7A/02 CPR

GANTE

Pablo A. Gonzalez Garza
#500 Col. San Jerónimo
Monterrey, Nuevo León
Mexico.

ventas@gante.mx
gante.mx